


HIGH THERMAL STABILITY

PURE WHITE COLOR

ODOR FREE

APt 3 is for bookbinding practically odour free at processing temperature with excellent thermal stability. It is appropriate for bonding several coated papers as well. Recommended for high quality jobs on coated paper.

Properties

Viscosity (Brookfield sp. 27, 20 rpm) 170°C

3 800 ± 600 mPa.s

Melting temperature / STN 65 7060/

75 – 85°C

Time until Solid

4 - 5 s

Open time

est. 15s

Color

white

Method of application

by roller

Processing temperature

160 – 180°C

Processing conditions

Processing temperature

160 -180°C (on roller)

Material

18 - 20°C

Ambient temperature

18 - 20°C

Storage conditions



Keep in original package



Temp. up to 30°C



Protect from direct sunlight